



#### IMPERSTOP "RR" con rivestimento ritardante

Nastro a rigonfiamento in bentonite per l'impermeabilizzazione economica di riprese getto.

Il nastro a rigonfiamento in bentonite Imperstop "RR" si distingue per un nuovo speciale rivestimento brevettato che ritarda di 2-3 giorni un prematuro rigonfiamento dovuto a pioggia.

Lo speciale rivestimento agisce in funzione del valore di pH. La pioggia con valore di pH 7 (neutrale) non scioglie il rivestimento per 2-3 giorni.

Lo speciale rivestimento viene sciolto chimicamente durante l'installazione con cemento fresco che invece ha un pH = 11 (basico, che può variare leggermente secondo la qualità del calcestruzzo).

#### DATI TECNICI IMPERSTOP "RR" 18x24

**Materiale:** Bentonite (Monimontonit), legante, stucco, additivi

**Rivestimento:** Polimero speciale, reagisce al valore di pH.

**Certificati di prove:** Hygiene Institut Gelsenkirchen (Certificato per acqua potabile) ACL Analytisch Chemisches Labor GmbH (diversi certificati di prove).

**Caratteristiche del prodotto:**

**Rivestimento:** Rivestimento speciale 2µm. Il valore di pH del cemento determina la soluzione chimica del rivestimento.

**Misure:** 18x24 mm. **Peso:** 750 g/m. **Volume di rigonfiamento** >500%. Speciale rivestimento brevettato.

#### IMPERSTOP "RR" with retardant coating

Bentonite re-inflating tape for low-cost waterproofing connecting concrete castings.

The Imperstop "RR" inflating bentonite tape stands out for its new special patented coating that retards premature inflation due to rain by 2-3 days.

The special coating acts according to the pH value. Rain with a pH value of 7 (neutral) will not dissolve the coating for 2-3 days.

The special coating is chemically dissolved during installation with fresh cement, which instead has a pH value=11 (alkaline, it may vary slightly according to the quality of the concrete).

#### TECHNICAL DATA FOR IMPERSTOP "RR" 18x24

**Material:** Bentonite (monimontonit), binder, filler, additives

**Coating:** special polymer, reacts to the pH value.

**Test certificates:** Hygiene Institut Gelsenkirchen (drinking water certificate) Acl Analytisch Chemisches Labor GmbH (various test certificates).

**Product characteristics:**

**Coating:** special 2µm coating. The cement's pH value determines the coating's chemical solution.

**Size:** 18x24 mm. **Weight:** 750 g/m. **Inflating volume** >500%. (special patented coating).

## Waterstop bentonitico "RR" / "RR" bentonite Waterstop

Codice Code	Denominazione commerciale Name	A mm	h mm	M Lm
490-010-200-018	Imperstop "RR" 24x18 con rivestimento ritardante / with retardant coating	24	18	20